



grupo estucalia

+34 968 862 467
www.monocapas.com

DATA SHEET

ONE COAT MORTAR SCRAPING/RASPADO

Ref. OC-CSIV-W2



Product made from high strength white cement, selected aggregates, organic additives and pigments

SUPPORTS

The supports must be stable, resistant, clean of dust, healthy, without releasing agents, moss or any other product that remains adherent. Do not apply on plaster or paint. In case of heat, wind or on very absorbent supports, it is recommended to moisten the support and wait for the disappearance of the water film. On low porous substrates, apply a primer (EUROFIX) or improve the roughness by mechanical means.

METHODOLOGY OF USE

Mix with 20-22% water, manually or mechanically, until a homogeneous and manageable mixture is obtained. Let the mortar knead for a few minutes and spread with a trowel or spray machine (specific for mortars) with a minimum thickness of 10mm. Let the mortar dry for 4-6 depending on the weather, and proceed to scrape it with the proper tools. After a few days it is recommended to brush the surface to remove particles that have been loose.

TECHNICAL DATA

Apparent density of non-compacted powder (Kg/m3)	1500 ± 100
Calcination residue (Ashes) at 450°C	8,8 ± 0,5
Calcination residue (ashes) at 900°C	63,4 ± 0,5
Residue on 1 mm sieve (UNE 7050-97), %	1,1± 0,2
Residue on 125 mm Sieve (UNE 7050-97), %	62,5 ± 1,0
Apparent density of the material in paste (Kg/m3)	1800 ± 50
Power or water holding capacity, %	90,8 ± 1,0
Apparent density of hardened material (Kg/m3)	1650 ± 100
Flexural strength N/mm ²	4
Resistance to Compression, N/mm ²	13
Retraction to drying, mm/m ²	0,23 ± 0,05
Capillarity (C), Kg/m ² min ^{1/2}	0,15± 0,1
Adherence	>0,5
Adhesion on smooth concrete, MPa	0,34 ± 0,2

The instructions for use do not imply any commitment for the manufacturer, nor do they free the consumer from the examination and verification of the product for its correct application. The liability of the manufacturer will be limited, in any case, to the value of the merchandise used.

CHARACTERISTICS:

Waterproof coating.
Permeable to water vapor, allowing the support to breathe.
Applicable in exterior and interior.
Direct plastering without the need for plastering
Easy workability
Very fluffy

CONSERVATION:

12 months from the date of manufacture, in the original closed container and protected from moisture.

PRESENTATION:

Sacks of 25 Kg. Palets of 1400 kg (56 sacks).

COLOR RANGE

Realization in a wide range of colors
(+175 colors)