



# grupo estucalia

+34 968 862 467  
www.monocapas.com

## DATA SHEET

### JOINT GROUT KOLATEC

Ref. CG2 AW UNE-EN 13888



Colored mortar for joints up to 15 mm. with a wide range of colors. Waterproof, without shrinkage and easy to clean. Mortar based on selected aggregates, white cement, resins, pigments and additives. Mortar for application in the form of paste for joints between tiles up to 15 mm. In pavements and coatings, both indoors and outdoors.

#### SUPPORTS

The joints between tiles must be clean and dry, and it is advisable that at least 36 hours have elapsed since the laying of the pavement, according to climatic conditions. If the pavements or coatings to be grout are porous or rough, it is advisable to protect them with a primer that facilitates their cleaning and to prevent them from staining or for the pigment to enter the micropore of the polish.

#### METHODOLOGY OF USE

Mix with water (25, -% approx.) And beat slowly by hand or mechanically (500 rpm) until a homogeneous paste is obtained, leaving it to rest for 2-3 minutes. Proceed to fill the joints with rubber trowel, filling gun or other suitable tool, pressing the dough to fill completely. Once the material begins its hardening, proceed to perform the final finish, with wet sponge or llaguero. When the material is completely hardened, proceed to the final cleaning with a damp cloth.

#### TECHNICAL DATA

#### CHARACTERISTICS:

High hardness  
Intense color  
Easy cleaning  
Low Water Absorption  
Exterior and interior

#### CONSERVATION:

12 months from the date of manufacture, in the original closed container and protected from moisture.

#### PRESENTATION:

Sacks paper or plastic of 5kg - 25kg

#### COLOR RANGE

+25 colors expandable according to customer demand.

#### PERFORMANCE

1,5 Kg / m<sup>2</sup>

#### TYPE OF ASSAY

#### RESULT

CLASSIFICATION ACCORDING TO DEGREE OF COMBUSTION	M 0
RESISTANCE TO FLEXION +28 DAYS	> 2,5 N/mm <sup>2</sup>
COMPRESSION RESISTANCE +28 DAYS	> 15 N/mm <sup>2</sup>
ABRASION	< 1000 mm <sup>3</sup>
ABSORPTION WATER +30 MIN.	< 2 g
ABSORPTION WATER +4 HOURS	< 5 g
APPARENT DENSITY POWDER PRODUCT	1,1 +- 0,2 g/cm <sup>3</sup>
APPARENT DENSITY PRODUCT IN PASTA	1,3 +-0,2 g/cm <sup>3</sup>
APPROXIMATE PERFORMANCE (BALDOSA 20x30 CM BOARD 10x10 MM)	1,5 Kg/m <sup>2</sup>
ADMITTED THICKNESS	12/15 mm.

The instructions for use do not imply any commitment for the manufacturer, nor do they free the consumer from the examination and verification of the product for its correct application. The liability of the manufacturer will be limited, in any case, to the value of the merchandise used.

Camino Viejo de Fortuna, 40 · 30148 · Apartado Correos 162 · Matanzas-Santomera (Murcia)  
T.: 968 862 467 · 663 519 854 · e-mail: estucalia@monocapas.com