



# grupo estucalia

+34 968 862 467  
www.monocapas.com

## DATA SHEET

### **GLUE CEMENT KOLATEC -C2-**

Ref. C2 UNE EN12004



Improved Cement Adhesive for Ceramic tiles with medium surface absorption. Open time, No off-hook. For the laying of direct tiling on the brick factory and concrete blocks, without the need for prior plastering and in floors with irregular backgrounds. Application in interior and exterior of ceramic pieces of average absorption and in Pools.

#### **SUPPORTS**

The supports must be stable, resistant, clean of dust, healthy, without releasing agents, moss or any other product that remains adherent. Do not apply on plaster or paint. Case of realizing recercados with Kolatec, of more than 15 mm. of thickness, do not make the ceramic application before 48 hours, until the screed has sufficiently hardened.

#### **METHODOLOGY OF USE**

Mix with 18-20% water, manually or mechanically, until a homogeneous and manageable mixture is obtained. Let the mortar knead for 5 minutes. In normal applications, the solid ceramic piece is placed, achieving better adherence if a well-compacted first layer is applied on the wall. In pavements, spread with a trowel and apply, always respecting the joints between ceramic plates and construction. In medium format pieces it is advisable to apply double gluing.

#### **TECHNICAL DATA**

| <b>TYPE OF ASSAY</b>                  | <b>RESULT</b>           |
|---------------------------------------|-------------------------|
| INITIAL ADHERENCE                     | <b>1 N/mm2.</b>         |
| ADHERENCE AFTER 20 Mnts.              | <b>0,5 N/mm2.</b>       |
| ADHERENCE AFTER IMMERSION WATER:      | <b>1 N/mm2.</b>         |
| ADHERENCE AFTER AGING HEAT:           | <b>1 N/mm2.</b>         |
| ADHERENCE AFTER ICE / DEFROST CYCLES: | <b>1 N/mm2.</b>         |
| APPARENT DENSITY POWDER PRODUCT       | <b>1,4 +- 0,2 g/cm3</b> |
| APPARENT DENSITY PRODUCT IN PASTA     | <b>1,7 +-0,2 g/cm3</b>  |
| APPROXIMATE PERFORMANCE               | <b>4 Kg./m2. aprox.</b> |
| ADMITTED THICKNESS                    | <b>0,6 / 2 Cm.</b>      |

#### **CHARACTERISTICS:**

Adhesion of ceramic pieces with medium-high absorption degree.  
Application in interiors and exterior pavements  
No drop-off  
Suitable for swimming pools

#### **CONSERVATION:**

12 months from the date of manufacture, in the original closed container and protected from moisture.

#### **PRESENTATION:**

Bags of 25 Kg. Palets of 1400 kg (56 bags).

#### **COLOR RANGE**

Normally white, possibility gray color on request.

#### **PERFORMANCE**

4 Kg / m2

The instructions for use do not imply any commitment for the manufacturer, nor do they free the consumer from the examination and verification of the product for its correct application. The liability of the manufacturer will be limited, in any case, to the value of the merchandise used.

Camino Viejo de Fortuna, 40 · 30148 · Apartado Correos 162 · Matanzas-Santomera (Murcia)  
T.: 968 862 467 · 663 519 854 · e-mail: estucalia@monocapas.com